

TEST REPORT

No.: GZMR110305852

Date: Apr 12.2011

Page: 1 of 3

YUHE GLASS TRADE CO., LTD DONGGUAN CITY NO.109, HONGTU ROAD, SCI, & TECH, PARK, NANCHENG ZONE, DONGGUAN CITY, GUANGDONG PROVINCE, P.R.C

The following sample(s) was/ were submitted and identified on behalf of the client as:

: FLOAT TEMPERED GLASS / 300×300×12mm Sample Name

SGS Ref No GP110320092-22.13

Test Performed Selected test(s) as requested by applicant

Date of Receipt : Mar 18,2011

Test Period Mar 18,2011 to Apr 02,2011

Test result(s) : Please refer to the following page(s)

*******To be continue******

Signed for and on behalf of SGS-CSTC Ltd.

May Huo

Engineer

ned by the Companyunder is: General Conditions of Service printed overleaf or available on request and accessible at http://www.egs.com/terms.andconds. In the limitation of Tability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained her indexings at the time of its intervention only and within the limits of Client's instructions, if say The Company's sole responsibility is to its Client and its properties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized attention, forget interventions are the second of the law.

1 (96-20)82155555 1 (86-20)82075080 • sgs.china@sgs.com



TEST REPORT

No.: GZMR110305852

Date: Apr 12.2011

Page: 2 of 3

Test result:

Sample description: Glass

No.	Test item	Test method	Test condition	Result	Requirement	Conclusion
1	Fragmentation test	BS 3193:2008 Annex A	Specimen: 300×300×11.80mm	Number of particles: 100	Number of particles shall be not less than 60.	Pass
2	Thermal shock test	BS 3193:2008 Annex B	Specimen temperature: 185℃ Tube internal diameter: 5mm Specimen: 300×300×11.80mm	No fracture.	Glass panels shall not fracture.	Pass
3	Impact test	BS 3193:2008 Annex C	Specimen: 300×300×11.80mm Hammer weight: 1.8kg Height: 150mm	No fracture.	Glass panels shall not fracture.	Pass

*******To be continued******

In is issued by the Companyunder & General Conditions of Service printed overleaf or available on request and accessible at http://www.ags.com/ferms.and.conditions, in is drawn to the limitation of lability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained here or contained the services of the first of the label of the services of t

GZMR



TEST REPORT

No.: GZMR110305852

Date: Apr 12.2011

Page: 3 of 3

Sample Photo:



*******End of report******

In is issued by the Companyunider & General Conditions of Service printed overlaaf or available on request and accessible at http://www.aga.com/terms.andconditions.

In is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained here on formation only and within the limits of Client's instructions, if any The Company's sole responsibility is to its Client and this best not be pastles to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or of the contemps appearance of this document is unlawful and offenders may be prosecuted to the full estextent of the law.

Wise stated the results shown in this test reported contylic the sample(s) tested and such sample(s) are retained for 30 days only. This document cannot be reproduced to the processor of the Company.

GZMR